



Quikcote Victoria Plaster Technology Pty Ltd ABN 76 078 391 545
26–30 Fleet Street Somerton, Victoria 3062
Factory 9303 7791 Fax 9303 7792
Email info@quikcote.com.au Web www.quikcote.com.au

Quikcote Colorcote is a cementitious based, polymer enhanced product used as the final coat or applied finishing coat, after your project has been rendered.

Quikcote Colorcote is different from most other applied finishes because of the natural products being used in the manufacturing process. Being sand and cement based this lets the product absorb and release water retention at will, which will naturally strengthen and produce a unique Mediterranean like finish.

Quikcote Colorcote comes in various colors (samples on request), and is packaged in 18kg bags in a fine or course finish.

Quikcote Colorcote is suitable for:

- Masonary surfaces
- Rendered surfaces
- Cement sheet application, provided it has already been rendered with Quikpatch)

SURFACE PREPARATION

To ensure correct adhesion, surfaces must be suitably flat and clean ie: free of contaminants such as grease, waxes, paint and any oil based substances.

APPLICATION

Colorcote when mixed should be added to approximately 3-4 litres of water using entire 18kg. of product.
Mixing to be done by drilling product to a creamy consistency, let slake for 5 to 10 minutes, and re-drill product, do not add any more water. It will come back wetter when re-drilled.

1. Apply Colorcote with a steel trowel laying on tight to wall.
2. Work the product with either plastic float or polystyrene float to achieve required finish.
3. To achieve a sand finish effect a sponge float is required, floating in a circular motion.

COVERAGE

Depending on surface application, approximately 8 to 12 metres.

TECHNICAL DATA

Specific Gravity: 1.86 kg/lt

Odor: Nil

Base: Cement

Surface Finish: Medium

Weather Resistance: High

PH: 11

Viscosity of Mix: (CPS) 95,000

GUARANTEE:

All products are guaranteed for seven years under *normal conditions.

This product should be used in accordance with directions which are only a guide. Quikcote accepts no responsibility for inappropriate use or faulty workmanship. All mineral earth based aggregate /course filler based renders and textures will contain a low percentage of carbon and/or ferrous contaminants and can occasionally spot the surface. All care is taken in raw material selection to minimize such effects. Quikcote accepts no responsibility for this occasional occurrence.

IDENTIFICATION

Product Name: Colorcote

UN Number: na

Poisons Schedule Number: na

Purpose: Surface Coating

PHYSICAL DESCRIPTION

Appearance: coloured

Vapor Pressure: na

Specific Gravity: 1.86 @ 25 Degrees Celsius

Flammability: na

Solubility: Water Soluble

HAZARDOUS INGREDIENTS

Sand >50%

Cement >30%

Pigment = variable

Proprietary additives (non hazardous) <20%

Remaining products are not deemed to be hazardous and are commercially confidential.

HEALTH HAZARD & FIRST AID INFO

- **SKIN CONTACT:**

Prolonged exposure may cause skin irritation:

Wash off with water.

- **EYE CONTACT:**

May cause pain: Irrigate with water for at least 15 min.

- **IF SWALLOWED:**

Single dose oral toxicity is low BUT do not induce vomiting. DO call a doctor and transport to emergency facility for further instructions.

- **IF INHALED:**

Prolonged inhalation may cause irritation:

Ensure adequate ventilation.

- **ENSURE SAFETY GLASSES ARE WORN FOR EYE PROTECTION**

- **GLOVES, BOOTS AND OVERALLS SHOULD BE WORN FOR PROLONGED CONTACT.**

SPILLS: SMALL SPILLS: SHOULD BE MOPPED UP OR SOAKED UP . LARGE SPILLS: SHOULD BE CONTAINED. AVIOD SPILLAGE INTO WATER SUPPLIES.

CLEAN UP

Warm water clean –up prior to drying.