

Quikcote Flexipatch is a high polymer cementitious based, highly flexible acrylic render, giving superior strength.

Quikcote Flexipatch has been manufactured to give extreme strength, durability and long term weather resistance.

Quikcote Flexipatch can be used for many different applications due to its bonding strength and flexibility. Can be used to rejuvenate old and new surfaces.

Quikcote Flexipatch is suitable for:

- Masonary surfaces
- Rendered surfaces
- Cement sheet application.
- CSR \$ Hardies.
- Polystyrene Application
- Over painted surfaces, *provided paint substrate is stable, keep in mind that Flexipatch is bonding to the paint, not what the paint is bonded to.*

SURFACE PREPARATION

To ensure correct adhesion, surfaces must be suitably flat and clean ie: free of contaminants such as grease, waxes, paint and any oil based substances.

APPLICATION

A.A.C sheet recommended alkaline resistant mesh be used for jointing , giving added strength and will not rot like other bandages or mesh.

1. Apply a bedding coat into joints and let dry.
2. Apply armororing first coat to entire surface of project, finishing off with styrene or Perspex float.
3. Final coat to be applied on setting of the first coat, finish off with styrene float.
4. Use Quikcote Colorcote as a preferred finish or a suitable products to achieve desired look.

COVERAGE

On smooth surface :approx 5 -10 sq. metres.

TECHNICAL DATA

Specific Gravity: 1.86 kg/lt
Odor: Nil
Base: Cement
Surface Finish: Medium
Weather Resistance: High
PH: 11
Viscosity of Mix: (CPS) 95,000

GUARANTEE:

All products are guaranteed for seven years under *normal conditions.

This product should be used in accordance with directions which are only a guide. Quikcote accepts no responsibility for inappropriate use or faulty workmanship. All mineral earth based aggregate /course filler based renders and textures will contain a low percentage of carbon and/or ferrous contaminants and can occasionally spot the surface. All care is taken in raw material selection to minimize such effects. Quikcote accepts no responsibility for this occasional occurrence.

IDENTIFICATION

Product Name: Flexipatch render
UN Number: na
Poisons Schedule Number: na
Purpose: Surface Coating

PHYSICAL DESCRIPTION

Appearance: Off White
Vapor Pressure: na
Specific Gravity: 1.86 @ 25 Degrees Celsius
Flammability: na
Solubility: Water Soluble

HAZARDOUS INGREDIENTS

Sand >50%
Cement >35%
Proprietary additives (non hazardous) <15%

Remaining products are not deemed to be hazardous and are commercially confidential.

HEALTH HAZARD & FIRST AID INFO

• **SKIN CONTACT:**

Prolonged exposure may cause skin irritation:
Wash off with water.

• **EYE CONTACT:**

May cause pain: Irrigate with water for at least 15 min.

• **IF SWALLOWED:**

Single dose oral toxicity is low BUT do not induce vomiting. DO call a doctor and transport to emergency facility for further instructions.

• **IF INHALED:**

Prolonged inhalation may cause irritation:
Ensure adequate ventilation.

• **ENSURE SAFETY GLASSES ARE WORN FOR EYE PROTECTION**

• **GLOVES, BOOTS AND OVERALLS SHOULD BE WORN FOR PROLONGED CONTACT.**

SPILLS: SMALL SPILLS: SHOULD BE MOPPED UP OR SOAKED UP . LARGE SPILLS: SHOULD BE CONTAINED. AVIOD SPILLAGE INTO WATER SUPPLIES.

CLEAN UP

Warm water clean –up prior to drying.