



Quikcote Victoria Plaster Technology Pty Ltd ABN 76 078 391 545  
26–30 Fleet Street Somerton, Victoria 3062  
Factory 9303 7791 Fax 9303 7792  
Email [info@quikcote.com.au](mailto:info@quikcote.com.au) Web [www.quikcote.com.au](http://www.quikcote.com.au)

**Quikcote Quikpatch** is a high polymer cementitious based Acrylic Render.

**Quikcote Quikpatch** has been manufactured to give extreme strength, durability and long term weather proofing.

**Quikcote Quikpatch** can be used for many different applications due to its bonding strength and flexibility. It can be used to rejuvenate old and new surfaces.

**Quikcote Quikpatch** is suitable for:

- All Masonary surfaces
- Rendered surfaces
- Cement sheet application eg:
- Blue board, C.S.R & Hardies
- Polystyrene Application

#### **SURFACE PREPARATION**

To ensure correct adhesion, surfaces must be suitably flat and clean ie: free of contaminants such as grease, waxes, paint and any oil based substances.

#### **APPLICATION**

Exterior cement sheet: Recommend alkaline resistant mesh be used for jointing, giving more strength and will not rot like other bandages or mesh.

1. Apply a bedding coat of flexipatch with mesh into joints and let dry.
2. Apply armoruring first coat of Quikpatch to entire surface of project, finishing off with styrene or Perspex float.
3. Final coat to be applied on setting of first coat, finish off with styrene float.
4. Use Quikcote Colorcote as final finish or suitable product to achieve desired finish.

For **Styrene Application**, please contact Quikcote for information.

#### **COVERAGE**

On smooth surface : approx 5-10sq. metres.

#### **TECHNICAL DATA**

Specific Gravity: 1.86 kg/lit

Odor: Nil

Base: Cement

Surface Finish: Medium

Weather Resistance: High

PH: 11

Viscosity of Mix: (CPS) 95,000

#### **GUARANTEE:**

All products are guaranteed for seven years under \*normal conditions.

This product should be used in accordance with directions which are only a guide. Quikcote accepts no responsibility for inappropriate use or faulty workmanship. All mineral earth based aggregate /course filler based renders and textures will contain a low percentage of carbon and/or ferrous contaminants and can occasionally spot the surface. All care is taken in raw material selection to minimize such effects. Quikcote accepts no responsibility for this occasional occurrence.

#### **IDENTIFICATION**

Product Name: Quikpatch

UN Number: na

Poisons Schedule Number:na

Purpose: Surface Coating

#### **PHYSICAL DESCRIPTION**

Appearance: Off White

Vapor Pressure: na

Specific Gravity: 1.86 @ 25 Degrees Celsius

Flammability: na

Solubility: Water Soluble

#### **HAZARDOUS INGREDIENTS**

Sand >50%

Cement >30%

Proprietary additives (non hazardous) <20%

***Remaining products are not deemed to be hazardous and are commercially confidential.***

#### **HEALTH HAZARD & FIRST AID INFO**

##### **• SKIN CONTACT:**

Prolonged exposure may cause skin irritation:

Wash off with water.

##### **• EYE CONTACT:**

May cause pain: Irrigate with water for at least 15 min.

##### **• IF SWALLOWED:**

Single dose oral toxicity is low BUT do not induce vomiting. DO call a doctor and transport to emergency facility for further instructions.

##### **• IF INHALED:**

Prolonged inhalation may cause irritation:

Ensure adequate ventilation.

- **ENSURE SAFETY GLASSES ARE WORN FOR EYE PROTECTION**

- **GLOVES, BOOTS AND OVERALLS SHOULD BE WORN FOR PROLONGED CONTACT.**

**SPILLS: SMALL SPILLS: SHOULD BE MOPPED UP OR SOAKED UP . LARGE SPILLS: SHOULD BE CONTAINED. AVIOD SPILLAGE INTO WATER SUPPLIES.**

#### **CLEAN UP**

Warm water clean –up prior to drying.